

n-Type Thermoelectric Properties of Single-walled Carbon Nanotubes encapsulating Molecular Dopants

Yu Iihara,¹ Tsuyoshi Kawai,¹ Yoshiyuki Nonoguchi,^{1,2}

¹ Graduate School of Materials Science, Nara Institute of Science and Technology,
Ikoma, Japan

² JST PRESTO, Kawaguchi, Japan

n-Type single-walled carbon nanotubes (SWNTs) have been investigated for the development of flexible p-n junction devices including solar cells[1] and FETs[2]. n-Type SWNTs have been regarded as unstable under ambient condition, which has motivated us to improve air-stability by means of molecular doping. We have recently demonstrated that adsorption of phosphine derivatives alters the sign of majority carriers of SWNTs from p-type to n-type[3]. However, phosphine-SWNT composites showed limited stability in air.

In this work, we report on the n-type doping and the stabilization of n-type SWNTs using the encapsulation of phosphine derivatives in SWNTs. The internal space of nanotubes is expected to suppress the oxidation. We chose 1,1'-Bis(diphenylphosphino)ferrocene (dppf) as a dopant since it shows a stable redox behavior. We prepared SWNTs encapsulating dppf (dppf@SWNTs) by heating dppf/SWNTs composite films at 200 °C *in vacuo*.

TEM observation revealed that dppf was encapsulated into SWNTs (Fig 1). The conductivity of the dppf@SWNTs was significantly higher than that of raw SWNTs, presumably due to the electron transfer from dppf to SWNTs. This composite showed comparatively high power factor ($195\mu\text{W}/\text{mK}^2$) with the negative Seebeck coefficient ($-51\mu\text{V}/\text{K}$) by encapsulation of dppf. Moreover, we found this n-type film was stable over 120 h in air[4].




Figure 1: TEM micrograph of dppf@SWNTs

References:

- [1] Taylor, A. D. *et al. Nano Lett.* **14**, 3388–3394(2014).
- [2] Dai, H. *et al. J. Am. Chem. Soc.* **123**, 11512–11513(2001).
- [3] Y. Nonoguchi *et al. Sci. Rep.* **3**, 3344(2013).
- [4] Y. Iihara *et al. Chem. Asian. J.* **11**, 2423–2427 (2016)..